



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDal Road, Minhang District, Shanghai, China

TECHNICAL DATA SHEET ®

0199 epoxy resin

0199 epoxy resin is A high molecular weight bisphenol A type solid epoxy resin produced by the reaction of liquid epoxy resin and bisphenol A.

Introduction

0199 epoxy resin is a kind of high molecular weight solid epoxy resin, mainly mixed with melamine, phenolic resin, polyester resin and other curing agent for baking paint field;It can also be used with isocyanate crosslinking agent as a binder in room temperature curing system or as a flow regulator in epoxy powder coatings.Top coat made from 0199 epoxy resin is suitable for metal decoration, tank inside and outside coatings, piping and other industrial applications.

Typical applications

This product is mainly suitable for the following occasions:

- General anticorrosion coatings
- Drying of the lacquer that bake
- Coil coating
- Insulating powder coating
- Can use coating

Typical Features

project	The numerical
appearance	Solid, no mechanical impurities
Colour and lustre (Gardner)	2 the following (1)
Epoxy equivalent (g/mol)	2200-4000.
Softening point (°C)	130-150.
Hydrolyzed chlorine (%)	0.1 the following
Volatile (%), 150°C/40min	0.5 the following

(1) 40% diethylene glycol butyl ether solution

Packaging and storage

0199 solid epoxy resin is available in 25 kg kraft paper bags.This epoxy should be stored in its original sealed packaging and in a cool, dry place.Storage should be far away from high temperature fire, avoid sunlight.Under the above conditions, the epoxy resin shall maintain its chemical properties for a period of at least 12 months from the date of manufacture.



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

Safety and disposal

The product shall be processed, used and disposed in accordance with the relevant safety and health laws and regulations of the country and the region. For detailed information on the safety of this product, please refer to the CORRESPONDING MSDS report of this product.

contact

Shanghai King Chemical Co.,Ltd
Address: ROOM CDEF, 9th Floor, Building D,
Weijing Center Tower, NO.2337 GuDai Road,
Minhang District, Shanghai, China 201199
Phone:+86-21-67817854
Fax: + 86-21-67817854
Web: <http://www.shkingchem.com> |

statement

The above information is based on reliable data. However, the specific application occasions and application conditions are not within our control. The curing formula and curing performance are for reference only. Customers can confirm their own formula and achieve physical property data according to their own needs.

This product should be used with caution and in accordance with the laws of the relevant region or country. It is not recommended to use on critical components of medical equipment in direct contact with the human body for extended periods of time.