



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

TECHNICAL DATA SHEET

Pigment Orange 13

1. Product Name

Trade Name: 1306A

C.I.: Pigment Orange 13

C.I. No.: 21110

CAS No.: 3520-72-7

Chemical Formula: C₃₂H₂₄Cl₂N₈O₂

Molecular Weight: 623.48

Chemical Group: Disazo Pyrazolone

2. Physical, Chemical and Resistance Properties

Appearance: Orange Powder

Shade: Similar to Standard

Bulk Density(lb/gal): 10.9-13.36

Moisture: ≤3%

Fineness(80 Mesh): ≤5%

PH Value: 3.2-7.0

Oil Absorption (ml/100g): 50±5

Water Soluble Matter (%): ≤1.5

Electric Conductivity (us/cm): ≤500

Acid Resistance: 5

Alkali Resistance: 4

Water Resistance: 5

Oil Resistance: 4

Alcohol Resistance: 4

Ester Resistance: 4

Benzene Resistance: 4

Ketone Resistance: 4

Soap Resistance: 4

Bleeding Resistance: 4

Migration Resistance: 4

Heat Resistance (°C): 160

Light Fastness (8=excellent): 7

3. Application



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

Application: printing,water-base coating,water-base ink,offset ink

Recommended Application: plastic, solvent-base coating,solvent-base ink

4. Packing

Packed in 25kgs Bag with Pallet.