



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

TECHNICAL DATA SHEET

Pigment Yellow 74

1. Product Name

Trade Name: 7402S

Color Index: Pigment Yellow 74

C.I. No.: 11741

CAS No.: 6358-31-2

Chemical Formula: C₁₈H₁₈N₄O₆

Molecular Weight: 386.36

Chemical Group: Monoazo

2. Physical, Chemical and Resistance Properties

Appearance: Yellow Powder

Shade: Similar to Standard

Bulk Density(lb/gal): 10.6-12.5

Moisture: ≤1.0%

Oil Absorption: 27-45

Fineness(80 Mesh): ≤5%

PH Value: 5.5-7.6

Water Soluble Matter (%): ≤1.5

Oil Absorption (ml/100g): 35-45

Electric Conductivity (us/cm): ≤500

Acid Resistance: 5

Alkali Resistance: 5

Water Resistance: 5

Oil Resistance: 4

Alcohol Resistance: 5

Ester Resistance: 4

Benzene Resistance: 4

Ketone Resistance: 4

Soap Resistance: 5

Bleeding Resistance: 5

Heat Resistance (°C): 160

Light Fastness (8=excellent): 6



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

3. Application

Application: water-base coating, water-base ink,solvent-base ink.

Recommended Application:solvent-base coating.

4. Packing

Packed in 25kgs Bag with Pallet.