



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

TECHNICAL DATA SHEET

Pigment Yellow 83

1. Product Name

Trade Name:HRS

C.I.: Pigment Yellow 83

C.I. No.: 21108

CAS No.: 5567-15-7

Molecular Formula: C₃₆H₃₂CL₄N₆O₈

Formula Weight: 818.49

Chemical Group: Diarylide

2. Physical, Chemical and Resistance Properties

Appearance: Yellow Powder

Shade: Similar to Standard

Bulk Density(lb/gal): 10.1-12.5

Moisture: ≤1.5

Fineness(80 Mesh): ≤5.0

PH Value: 4.4-6.9

Water Soluble Matter (%): ≤1.0

Oil Absorption (ml/100g): 39-98

Electric Conductivity (us/cm): ≤500

Acid Resistance: 5

Alkali Resistance: 5

Water Resistance: 5

Oil Resistance: 5

Alcohol Resistance: 5

Ester Resistance: 5

Benzene Resistance: 5

Bleeding Resistance: 5

Heat Resistance (°C): 220

Light Fastness (8=excellent): 5

3. Application

Application: water-base ink,solvent-base ink,offset ink.

Recommended Application: Printing, water-base coating. **4.**

Packing



Shanghai King Chemical Co.,Ltd

Tel: +86-21-67817854 Fax: +86-21-67817855

**Address: ROOM CDEF , 9th Floor, Building D, Weijing Center Tower
NO.2337 GuDai Road, Minhang District, Shanghai, China**

Packed in 25kgs Bag with Pallet.